

Technical Data Sheet

BS-3368 Ultimate D3 Wood Glue



Features

- ◆ Water-resistant D3
- ◆ Indoor & outdoor use
- ◆ Easy to spread
- ◆ High bond strength
- ◆ Fast curing
- ◆ Forms thin gapless layer when set
- ◆ Non-toxic, solvent free and low odour

Available Colours

- ◆ White (Wet)
- ◆ Clear (Dry)

Storage

- ◆ Store in a dry and cool place with temperature below +30°C.

Shelf life:

- ◆ 24 months

Packaging

- ◆ 125 g / bottle ~ 12/ box; 144/ carton
- ◆ 250 g / bottle ~ 12/ box; 72/ carton
- ◆ 500 g / bottle ~ 24/ carton

Product Specification

Appearance	: Viscous Liquid
Specific Gravity	: 1.05 - 1.10
Viscosity at 25 °C (Brookfield LV 3 @ 5rpm)	: 11,000 - 15,000 cps
Solid Content	: 48.0 - 50.0%
pH	: 3.0 - 4.0
Wet Tack	: Aggressive
Flammability	: Non Flammable

Description

A D3-grade wood glue, specially formulated for woodworking applications that require resistance to short-term submersion. It offers fast setting, superior bonding strength, and versatility with various porous substrates for both indoor and outdoor use. It is non-toxic, solvent-free, and easy to clean up with water.

Applications

Idea for indoor and outdoor wood joining, furniture repair, wooden frames, and woodworking projects that require short-term submersion resistance. **Note:** Not recommend for continuous submersion or use below the waterline.

Directions

1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
2. Apply the adhesive on both surfaces if the material is porous. Press together firmly and leave to dry.
3. Replace cap after use and store in a cool, dry place.

Caution

Keep out of reach of children. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.